



OIL REPORT

LAB NUMBER: G55080
REPORT DATE: 1/15/2015
CODE: 63/501

UNIT ID: 13 ACCORD
CLIENT ID:
PAYMENT: Prepaid

UNIT
MAKE/MODEL: Honda 2.4L K24W1 Earth Dreams
FUEL TYPE: Gasoline (Unleaded)
ADDITIONAL INFO:

OIL TYPE & GRADE: Amsoil Signature Series 10W/30
OIL USE INTERVAL: 12,237 Miles

CLIENT
SCOTT HIBBELER
TYLER, TX

PHONE: (903)
FAX:
ALT PHONE:
EMAIL: @yahoo.com

COMMENTS
SCOTT: Here's another nice report for your Accord. No measurable fuel was found and the TBN was plenty strong at 5.6, so there's enough active additive remaining for a longer run next time. Your wear metals look fantastic too. Most of them read lower after a much longer oil run, so your engine is wearing nicely at 34,362 miles, and it didn't mind the longer oil run either. You're getting better than average wear after running nearly 5,000 miles longer on the oil - fantastic! The viscosity was a little low for a 10W/30, but that's not a problem. Try 14K miles next. Nice!

ELEMENTS IN PARTS PER MILLION	MI/HR on Oil	12,237	UNIT / LOCATION AVERAGES	9,693	12,432				UNIVERSAL AVERAGES
	MI/HR on Unit	34,362		22,125	12,432				
	Sample Date	01/06/15		06/29/14	11/05/13				
	Make Up Oil Added	0 qts		1 qt	0 qts				
ALUMINUM	7	12		11	17				7
CHROMIUM	0	0		0	0				0
IRON	10	17		16	26				12
COPPER	3	8		4	16				3
LEAD	0	0		0	1				0
TIN	1	0		0	0				1
MOLYBDENUM	145	328		183	656				118
NICKEL	1	0		0	0				0
MANGANESE	1	5		4	10				3
SILVER	0	0		0	0				0
TITANIUM	0	0		0	0				0
POTASSIUM	2	7		10	9				3
BORON	80	103		114	114				56
SILICON	12	44		18	102				15
SODIUM	5	8		6	13				7
CALCIUM	3444	2776		2963	1921				1844
MAGNESIUM	14	14		15	13				265
PHOSPHORUS	638	642		602	686				637
ZINC	730	724		694	749				696
BARIUM	0	1		0	3				0

Values
Should Be*

PROPERTIES	SUS Viscosity @ 210°F	56.0	58-65	56.5	48.3			
	cSt Viscosity @ 100°C	9.08	9.7-11.9	9.21	6.74			
	Flashpoint in °F	385	>375	400	380			
	Fuel %	<0.5	<2.0	<0.5	TR			
	Antifreeze %	0.0	0.0	0.0	0.0			
	Water %	0.0	<0.1	0.0	0.0			
	Insolubles %	0.3	<0.6	0.2	0.2			
	TBN	5.6	>1.0	5.3	0.4			
	TAN							
	ISO Code							

* THIS COLUMN APPLIES ONLY TO THE CURRENT SAMPLE

416 E. PETTIT AVE. FORT WAYNE, IN 46806 (260) 744-2380 www.blackstone-labs.com